

Estocure P

Concrete Curing Compound

Description

Estocure P is a liquid curing compound for the prevention of premature water loss in concrete.

Estocure P is applied to fresh concrete surfaces to form a fast dry, thin flexible and tough, impervious membrane which protects the concrete from rapid water evaporation during initial curing stages, thereby assisting towards obtaining maximum strength, durability and helping towards the elimination of shrinkage cracks and surface dusting

Uses

Estocure P is particularly useful in large areas of exposed concrete such as:

- Roof & bridge decks
- Aprons, hard standing & retaining walls
- Pre-stressed beams and piers, etc.
- Highways, runways and taxiways
- Column, beam & precast unit

Advantages

- Enable cement to hydrate better
- One time application reduces labour cost
- Reduce surface shrinkage & cracking
- Save time and eliminates need for damp Hessian and polythene sheet
- Disintegrated under ultra violet light or abrasion.
- Proven and predictable performance

Standards Compliance

- **BS 7542:1992**
- **ASTM C156-93**
- **ASTM C309-93 Type 1**
- **BS 5750**

Physical Properties

Curing Efficiency Index, BS 7542, 1992	> 45%
Loss of Water In 72 Hours (kg/m ²), ASTM C156-93	< 0.70
Liquid Membrane Forming Compound For Curing Concrete, ASTM C309-93	Comply
Specific Gravity at 25°C	1.02 -1.05
Colour	Milky White
Dry Film Colour	Clear Film
Dry Film @30 °C (approx.)	1-2hrs

Application Instructions

Application

Estocure P is supplied ready to use and should not be diluted with any forms of solvent / water. Stir well before use.

Estocure P is applied in a thin even coat using spray equipment to the fresh concrete immediately after the free surface water has evaporated. All loose particles should be removed and honeycomb to be repaired.

The nozzle of the spray should be held approximately 500mm from the surface and passed back and forth to effect complete coverage.

After application of **Estocure P**, it should be protected from rain for at least 3 hours.

Total disintegration of the membrane normally occurs after 5 weeks of application if the application rate is correct (5m²/litre).

Where subsequent surface treatment is to be undertaken before total disintegration of the membrane, **Estocure P** film shall be removed.

Estocure P should not be applied to dry concrete particularly on vertical surfaces or soffit of concrete, which may have partially dried out by being retained in shuttering. It is imperative that the concrete be well wetted before applying **Estocure P**. If this is not done, permanent staining will result.

Packing & Size

Estocure P	210 litre drum 20 litre pail
-------------------	---------------------------------

Coverage

Estocure P	5 m ² per litre
-------------------	----------------------------

Technical Support

Estop offers a comprehensive range of high performance, high quality of repair product for both new and existing concrete surfaces. In addition, the company offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

Storage

Estocure P has a shelf life of 12 months at ambient room temperature in unopened condition.

If stored in extreme heat locations the shelf life may be reduced.

Precaution

Estocure P should not be swallowed and avoid to be in contact with skin or eyes. Wear gloves and goggles for protection. If swallowed, seek medical attention immediately

Do not induce vomiting.

Additional Information

Estop manufactures and offers a wide range of complementary products, which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.

Important Note

Estop products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Estop endeavors to ensure that any advice, recommendation, specification or information in may give is accurate and correct, it shall not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.