

# Estotect E 230A

## Damp-Tolerant, Solvent Free Epoxy Resin Coating

### Description

**Estotect E 230A** is a solvent less epoxy coating and lining system for concrete and steel.

It is a two pack, solvent free epoxy resin material. It is supplied in pre-measured quantities ready for site mixing and use. The material cures to provide a smooth, tough and resistant finish. It is available in light grey.

### Uses

**Estotect E230a** is a protective coating for concrete and mild steel. It is particularly useful where concrete surfaces are damp and cannot be dried out. Its ultra high build properties allow a thickness of up to 400 micron to be achieved in single spray application. The cured film is corrosion, chemical and abrasion resistant and is suitable for application such as:

- Sewage works
- Basements
- Marine environments
- Tunnels
- Food processing factory,
- Laboratory,
- Hangars,
- Loading ramp,
- Kitchen,
- Workshop and clean room.

### Advantages

- Excellent resistance to corrosion, chemical, abrasion, impact and thermal shock
- Excellent bonding strength with suitable primers
- Low permeability to water and chloride ions.
- Low odour and food grade
- High build application
- Suitable for use in confined areas
- Can be applied directly to mild steel and concrete
- Smooth, glossy, easy to clean surface
- Can be applied on damp surfaces

### Design Criteria

**Estotect E230A** is design to be applied in two coats. To achieve the correct protective properties, **Estotect E230A** must be applied on to the substrate at the coverage rates recommended.

### Physical Properties

Finishing	Semi-gloss
No of components	2
Solid Content, %	>90
Recommended thickness / coat, microns	200 WFT
Pot Life:	1 hours (varies with temperature)
Dry time:	
Touch dry	2-3 hours @ 25°C
Recoat	12 hours @ 25°C
Open for traffic	24 hours @ 25°C
25°C	25°C
Fully cured:	
At 25°C	7 days

### Application Instructions

#### Surface preparation

Substrate shall be clean and free from laitance, loose particles and previous coatings. It can be prepare blast cleaning, water jetting and acid etching, wire brushing or grinding.

For steel substrates, it is ideally to blast cleaning to SA2½.

#### Application

The two parts of **Estotect E230A** shall be mix thoroughly until it obtained a homogeneous mixture, with a slow speed mixer.

**Estotect E230A** can be applied by brush or spray to give a uniform thickness. Faster rates of application are possible using airless spray equipment. It is recommended to apply in two coats system to achieve dry film thickness of 350 micron to 400 micron.

**ESTOTECT E230A SHALL NOT BE ADDED WITH WATER.**

#### Packing & Size

<b>Estotect E 230A</b>	5 litre pack
------------------------	--------------

#### Coverage

Theoretical coverage @ 200µ	Approx: 5m <sup>2</sup> / litre / coat
-----------------------------	--

**Technical Support**

Estop offers a comprehensive range of high performance, high quality of product for both new and existing concrete surfaces. In addition, the company offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

**Storage**

**Estotect E 230A** should be stored on pallets in cool and dry conditions. The product shelf life is of 12 months.

**Precaution**

For industrial use only. Avoid contact with eyes and skin, do not use without protective gears for eyes, hand. Product is not flammable.

**Additional Information**

Estop manufactures and offers a wide range of complementary products, which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.

**Important Note**

*Estop products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which may be obtained on request. Whilst Estop endeavors to ensure that any advice, recommendation, specification or information in may give is accurate and correct, it shall not, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.*